

## Description

Lexan Exell D OB FR sheet is an optical bright opal white grade with proprietary UV protection on both sides offering excellent weathering properties. With its excellent impact resistance it is an excellent candidate for a wide variety of building and construction applications, public transportation, as well as signage and lighting. Lexan Exell D OB FR sheet can be easily cold formed into gentle curves which makes it a good material choice for light diffusers, skylights, covered walkways, barrel vaults etc. Lexan Exell D OB FR sheet is thermoformable and can be thermoformed into the desired geometry whilst retaining the UV resistant coating specially developed for weather resistant applications.

## Typical Property Values ♦

Property	Test Method	Unit	Value
<b>Physical</b>			
Density	ISO 1183	g/cm <sup>3</sup>	1.25
Water absorption, 24 hours	ISO 62	mg	10
Water absorption, saturation /23°C	ISO 62	%	0.35
<b>Optical</b>			
Light transmission <sup>†</sup> )WH6DO600 [at 4.00mm]	ASTM-D1003	%	39
Light diffusion factor [at 4.00mm]	DIN 5036		0.86
<b>Mechanical</b>			
Tensile stress at yield 50 mm/min	ISO 527	MPa	60
Tensile stress at break 50 mm/min	ISO 527	MPa	70
Tensile strain at yield 50 mm/min	ISO 527	%	6
Tensile strain at break 50 mm/min	ISO 527	%	120
Tensile Modulus 1 mm/min	ISO 527	MPa	2300
Flexural stress at yield 2 mm/min	ISO 178	MPa	90
Flexural Modulus 2 mm/min	ISO 178	MPa	2300
<b>Impact</b>			
Charpy impact, notched	ISO 179/2C	kJ/m <sup>2</sup>	35
Izod impact, unnotched 23°C	ISO 180/4U	kJ/m <sup>2</sup>	NB
Izod impact, unnotched -30°C	ISO 180/4U	kJ/m <sup>2</sup>	NB
Izod impact, notched 23°C	ISO 180/4A	kJ/m <sup>2</sup>	65
Izod impact, notched -30°C	ISO 180/4A	kJ/m <sup>2</sup>	10
<b>Thermal</b>			
Vicat Softening Temperature, Rate B/120	ISO 306	°C	145
HDT/ Ae, 1.8 MPa edgew. 120*1*04/sp=100	ISO 75/Be	°C	138
Thermal Conductivity	ISO 8302	W/m °C	0.2
Coeff. of Thermal Expansion extr. 23-80°C	ISO 11359-2	1/ °C	7.10 <sup>-5</sup>
<b>Flammability</b>			
Glow Wire Test, 960°C,	IEC695-2-1	passes at	4 mm

♦ These property values have been derived from Lexan\* resin data for the material used to produce this sheet product. Variations within normal tolerances are possible for various colors. If minimum certifiable properties are required please contact your local SABIC Innovative Plastics representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on injection molded samples. All samples are prepared according ISO 294.

<sup>†</sup>) Light transmission value and light diffusion may vary by + or -4 %.

\* Trademarks of SABIC Innovative Plastics IP BV

## Optical properties

Gauge / color grade	Light Transmission (%)	Diffusion Factor
2 mm/ WH6DO600	pending	pending
3 mm/ WH6DO600	pending	pending
4 mm/ WH6DO600	39 ± 4%	0.86
5 mm/ WH6DO600	pending	pending
6 mm/ WH6DO600	pending	pending
8 mm/ WH6D2300	26 ± 4%	0.80
9.5 mm/ WH6D2300	26 ± 4%	0.80
12 mm/ WH6D2300	26 ± 4%	0.80

## UV protection

Lexan Exell D OB FR sheet has proprietary UV protected surfaces, giving excellent durability to outdoor weathering. The superior UV protected surface treatment is not affected by forming and fabricating and Lexan Exell D OB FR sheets are therefore backed by a 10 years warranty\* against yellowing, loss of light transmission and breakage.

\* ) see warranty for details.

## Fire performance

French Norm NF P92-505 M2 classification is available for Lexan ExellD OB FR sheet.

## Product availability

Lexan\* Exell D OB FR sheet is normally manufactured in the standard sizes listed below;

**Standard gauge:** 2, 3, 4, 5, 6, 8, 9.5, 12 mm

**Size:** 2050 x 3050, 2050 x 6050 mm

**Masking:** Top side/polished: co-ex opal white PE with print Bottom side/ polished: co-ex transparent PE



\* Trademark of SABIC Innovative Plastics IP BV

Americas:  
SABIC Innovative Plastics  
Specialty Film & Sheet  
One Plastics Avenue  
Pittsfield, MA 01201  
USA  
Tel. (1) (413) 448 5400  
Fax. (1) (413) 448 7506  
Toll free: 1-800 451 3147

Europe:  
SABIC Innovative Plastics  
Specialty Film & Sheet  
Plasticslaan 1  
NL - 4612 PX Bergen op Zoom  
The Netherlands  
Tel. (31) (164) 292911  
Fax. (31) (164) 293272

Pacific:  
SABIC Innovative Plastics  
Specialty Film & Sheet  
1266 Nanjing Road (W)  
16th Floor, Plaza 66  
200040 Shanghai, China  
Tel. (86) 21 6288 1088  
Fax. (86) 21 6288 0818

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com> AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of Sabic Holding Europe BV

\* Trademarks of SABIC Innovative Plastics IP BV

[www.sabic-ip.com](http://www.sabic-ip.com)

Latest update SABIC (01/08)